



PROPERTY	UNIT	100/150	TEST METHODS
Penetration @25°C, 100gm, 5sec	0.1MM	100-150	EN 1426
Softening Point, Ring & Ball	°C	39-47	EN 1427
Penetration Index	-	-1.5 to +0.7	EN12591-Annex A
Resistance to Hardening @163°C			
- Change in mass, Max	%Wt	0.8	EN 12607-1
- Retained Penetration, Min	0.1MM	43	
-Softening point after hardening, Min	°C	41	
Flash Point Cleveland open cup, Min	°C	230	EN ISO 2592
Solubility in CS ₂ , Min	%Wt	99.0	EN 12592
Kinematic Viscosity @135°C, Min	mm ² /s	175	EN 12595
Paraffin wax content, Max	%Wt	4.5	EN12606-2

Penetration Grade Bitumen. 100/150 is produced from the vacuum distillation of crude oil and is classified according to its penetration range. Bitumen 100/150 is a thermoplastic material which softens gradually as it is heated and hardens as it is cooled. This unique temperature/viscosity relationship is important when determining its performance parameters and application temperatures. Unlike modified binders, penetration grade bitumen acts as a Newtonian fluid at high in-service temperatures, which allows one to establish a temperature/viscosity relationship. Bitumen 100/150 is used in the construction of single seals, double seals and Cape seals, either as a tack coat or penetration spray. It is also used as the base bitumen for the manufacture of the majority of emulsions and polymer modified binders. Bitumen 100/150 fulfils the requirements for paving grade bitumen in accordance with EN 12591.

Packaging: New steel drums, reconditioned steel drums or eco-friendly poly bags. Weatherproof packaging

Storage and Handling Recommendations: Store in unopened containers. Storage temperature limits 1°C - 50°C. For normal operations, such as blending and transferring liquid bitumen, temperatures of 10°C - 40°C above the minimum pumping temperature are recommended.

Recommended Application Temperatures:

Asphalt Mixing Temperature : 150°C - 160°C

Asphalt Compacting Temperature : 135°C - 145°C.

For further information, please contact:

PP Softtech Pvt. Ltd.

Puri AANAND VILAS, T1- GFD, Sector 81,

Faridabad, Haryana 121004 India

Mail: prashant@ppsofttech.com

Phone: +91 9899895811