



PP Softtech Pvt. Ltd.

PRODUCT TECHNICAL DATA SHEET

BITUMEN AC-30

(Viscosity Grade)

TYPICAL PROPERTIES

| Property | Units | AC-30 | Test Methods |
|---|--------|-----------|--------------|
| Viscosity, 140°F (60°C) | P | 3000± 600 | ASTM D-2171 |
| Viscosity, 275°F (135°C), Min | cST | 250 | ASTM D-2171 |
| Penetration, 77°F (25°C), 100g, 5sec, Min | 0.1 MM | 30 | ASTM D-5 |
| Flash point, Cleveland open cup, Min | °C | 450(232) | ASTM D-92 |
| Solubility in trichloroethylene, Min | %Wt | 99 | ASTM D-2042 |
| Tests on residue from thin-film oven test: | | | |
| - Viscosity, 140°F (60°C), Max | P | 15,000 | ASTM D-2171 |
| - Ductility, 77°F (25°C), 5cm/min, Min | CM | 15 | ASTM D-113 |

For further information, please contact:

PP Softtech Pvt. Ltd.

Puri AANAND VILAS, T1- GFD, Sector 81,

Faridabad, Haryana 121004 India

Mail: prashant@ppsofttech.com

Phone: +91 9899895811